

EVERflow®

Made by MPC



TECHNICAL DATA SHEET

version v.03-12-2024



EVERTOP PU

TWO COMPONENT ALIPHATIC POLYURETHANE TOPCOAT (COLORED VERSION)



This two-component, colored, aliphatic solvent-based polyurethane coating provides a glossy finish and is designed for the protection of our waterproofing, roofing and traffic liquid systems. Once dry, it forms a durable, seamless, and continuous film with excellent adhesion and mechanical properties. It is highly resistant to weathering, extreme temperatures, and UV radiation.

For application in the following situations:

- Aliphatic protection for our waterproofing liquid membranes against UV solar rays, on flat and sloped roofs (vehicle traffic), and parking membranes
- UV stable coating for industrial and commercial flooring

Technical and chemical properties

Density ISO 1675 Viscosity ISO 2555	±1.20 g/cm ³ 2,000-2,300 cps
Solids Content ISO 1768 VOC content	±71% 326 g/L
Mixing ratio (in weight)	6.14: 1
Product Yield	185-371 sq. ft / kit (5-10 mils) 150 g/sqm/layer - 300 g/sqm/layer *depending on application method and conditions
Pot life Initial dry time Recoat time Cured time	±1 hour ±2 hours 2- 24 hours ±7 days
Application temperature range (substrate and environment) Use temperature range (environment)	5-35°C (41-95°F) -20-80°C (-4-176°F) Maximum environment humidity 80%
Application method	short-nap acrylic wool roller, by brush, or airless equipment
Packaging and color	4.3 kg A and 0.7 kg B (11 lbs.) Available in neutral, and matt gray RAL7042
Storage and shelf life	12 months in original containers in a dry environment 5-35°C (41-95°F). Keep away from direct sunlight, extreme heat/cold or moisture. Once opened, product must be used completely.

EVERflow®

Made by MPC



TECHNICAL DATA SHEET

version v.03-12-2024

Surface preparation for cement/concrete substrates:

Remove dust, dirt, grease, oil, and all other contaminants with proper cleaner/degreaser. Prepare the surface mechanically as per ICRI-CSP2 profile by diamond grinding to ensure removal of laitance, curing agents and sealers. The compressive strength of a newly poured concrete substrate must be at least 25 MPa (3635 psi) after 28 days of cure and at least 1.5 MPa (218 psi) tensile strength. Be careful with condensation (at least 3 degrees of the dew point). All cracks, holes and irregularities must be repaired with a crack filler prior to applying the coating.

Application method (classic application)

Open the containers, pour component B into the container of component A and mechanically mix the product using a low-speed drill (300-450 rpm) to reduce air entrapment and to obtain a homogeneous mixture. Apply the first layer with a short nap acrylic wool roller. The material should be applied undiluted. To achieve an anti-slip surface, broadcast the wet surface with silica sand at the consumption desired. Once dry, remove the non-adhering aggregate. Repeat this process as needed to reach the desired or recommended thickness.

Physical and Technical properties

Elongation at break (tested on a pu membrane) ISO 527-3	±95%
Adherence resistance UNE-EN 13892-8	3.5 MPa
Impact resistance, UNE-EN ISO 6272-1	>14.7 Nm at 1500 mm no damages, crater diameter 5.9 mm
Wear resistance, UNE-EN 13892-4	30 µm
Reaction to fire ISO-11925-2	Efl
Walkable (pedestrian/vehicular)	±12 hours / ±24 hours
Solar reflectance index (SRI) ASTM E1980-11	105.5 (white, RAL 9003)
Slip resistance UNE-EN 16165 (700g/sqm silica sand)	Rd=53 Class 3 (outside areas and pools)
Slip resistance UNE-EN 16165 Annex B/DIN 51130 (700g/sqm silica sand)	R12 (31° ramp test values)

*Results where performed in a laboratory setting at 23°C (73°F) and 50% RH, under controlled conditions. These values may vary depending on the application, climatology, or substrate conditions.

EVERflow®

Made by MPC



TECHNICAL DATA SHEET

version v.03-12-2024

General specification and restrictions

- A two-component, colored, aliphatic polyurethane solvent-based resin with a glossy finish, designed for the decoration, flooring, and protection of our waterproofing liquid systems.
- Once cured, it forms a durable, strong, seamless, and continuous film with excellent adhesion and mechanical properties, resistant to weathering, extreme temperatures, and UV radiation.
- It is suitable for use on various surfaces, including concrete, mortar, steel/metal, cement, plywood, ceramics, and as a topcoat for our waterproofing membranes (providing UV ray protection).
- It should be applied in dry conditions, ensuring that there is no moisture present on the surface to be coated or the substrate, either at the time of application or afterward (such as pressure from the phreatic water level (' hydrostatic')). If there is moisture in the substrate at the time of application, the process should be adjusted accordingly.
- The final product is obtained by thoroughly mixing both components in a 100% ratio. If only part of the product is used, ensure the ratio is maintained to preserve the product's optimal performance.
- To ensure consistent color, use the same batch for each application area to avoid color variations.

Warranty and disclaimer

Everflow® warrants that our products are free from manufacture defects in accordance with our quality control procedures. Any products proven defective are limited to the replacement of defective products or refund of the purchase price as determined by Everflow®. Please contact your local Everflow® sales representative for more information and warranty requirements.

The information and recommendations contained in this technical data sheet are based on reliable test results according to Everflow®. The data mentioned are specific to the material indicated. If used in combination with other materials, the results may be different. It is the responsibility of the user to validate the information therein and to test the product before using it. Everflow® assumes no legal responsibility for the results obtained in such cases. Everflow® assumes no legal responsibility for any direct, indirect, consequential, economic or any other damages except to replace the product or to reimburse the purchase price, as set out in the purchase contract.